

REPORT

3933 US ROUTE 11 CORTLAND, NEW YORK 13045

Order No. G101135449 Date: April 9, 2013

REPORT NO. 101135449CRT-001

TEST OF SAFETY GOGGLES

MODELS

ASPEN G15 | ASPEN GOLD MIRROR

RENDERED TO

VICSA SAFETY SA PINTOR CICARELLI 683 8950002 SAN JOAQUIN, CHILE

DATA REQUESTED

The client requested optical testing to Section 5 of ANSI Z87.1.

AUTHORIZATION

This test service was authorized by signed quote number 500446020.

REFERENCE DOCUMENTS: The following Test Standards were used in part or in total to test

each sample:

ANSI Z87.1 2010 American National Standard for Occupational and Educational

Personal Eye and Face Protection Devices

ASTM D1003 2007 Standard Test Method for Haze and Luminous Transmittance of

Transparent Plastics

DEVICES SUBMITTED

The samples were received by Intertek in undamaged condition, and were tested as received. The Intertek control numbers were 135449-01 and 135449-02

DATES OF TESTS

April 4 through April 5, 2013



EQUIPMENT LIST

		Control	Calibration	Calibration	
Equipment Used	Model Number	Number	Date	Due Date	
Optronics Spectroradiometer	OL750D	E288	04/04/13	04/05/13	
Gardner Hazemeter	XL211	N328	04/04/13	05/05/13	
Extech Hygrothermometer	445703	T1366	11/08/12	11/08/13	
Intertek 100ft Goniometer	NA	N060	08/14/12	08/14/13	

TESTS

Section 5.1.1 Optical Quality:

Lenses shall be free of striae, bubbles, waves and other visible defects which would impair their optical quality.

Section 5.1.2 Luminous Transmission:

Clear lenses shall have a luminous transmission of not less than 85%. Clear and Filter lenses shall be labeled in accordance with Table 4a of ANSI Z87.1. Plano and prescription lenses shall comply with Tables 6-10 of ANSI Z87.1 where applicable.

Section 5.1.3 Haze:

Clear and plano lenses shall not exhibit more than 3% haze.

Section 5.1.4 Refractive Power, Astigmatism, Resolving Power, Prism and Prism Imbalance:

Lenses shall meet the tolerances for Refractive Power, Astigmatism and Resolving power as specified in Table 1 of ANSI Z87.1. Lenses shall meet the tolerances for Prism and Prism Imbalance as specified in Table 2 of ANSI Z87.1.

Table 1: Tolerance on Refractive Power, Astigmatism and Resolving Power					
Protector	Refractive Power	Astigmatism	Resolving Power		
Spectacle	± 0.06 D	≤ 0.06 D	Pattern 20		
Goggle	± 0.06 D	≤ 0.06 D	Pattern 20		
Faceshield Windows	No Requirement	No Requirement	Pattern 20		
Welding Helmet Lenses	± 0.06 D	≤ 0.06 D	Pattern 20		

Table 2: Tolerance on Prism and Prism Imbalance					
Protector	Prism	Vertical Imbalance	Base In Imbalance	Base Out Imbalance	
Spectacle	≤ 0.50 ∆	≤ 0.25 ∆	≤ 0.25 ∆	≤ 0.50 ∆	
Goggle	≤ 0.25 ∆	≤ 0.125 ∆	≤ 0.125 ∆	≤ 0.50 ∆	
Faceshields	≤ 0.37 ∆	≤ 0.37 ∆	≤ 0.125 ∆	≤ 0.75 ∆	
Welding Lenses	≤ 0.50 ∆	≤ 0.25 ∆	≤ 0.25 ∆	≤ 0.75 ∆	

Date: April 9, 2013



RESULTS OF TEST

Section 5.1.	1 Optical Quality:								
		Model Number		Defect	Defects		F	Pass/Fail	
135449-		ASPEN G15 ASPEN GOLD		None)			Pass Pass	
135449-		MIRRO		None	•			1 400	
Section 5.1.2	2 Luminous Trans	smissior	<u>n:</u>						
					cent Trans			(=a.a	
Control Nun				Left Eye		Right Eye	e Pa	ss/Fail/NA	
		ASPEN G15 ASPEN GOLD		14.6		14.6		NA	
135449-0	_	RROR	.ل	10.5	10.2			NA	
Section 5.1.3	3 Haze:								
					Percent H	łaze			
Control Nun		el Numb			Left Eye Right		Pa	Pass/Fail/NA	
135449-0	449-01 ASPEN G15 ASPEN GOLD			0.70	0.84			Pass	
135449-0		RROR	_	1.46		1.53		Pass	
Section 5.1	4 Refractive Pow	or Astic	ımatiem	Resolving Po	ων _Θ r				
Control	+ Nellactive I OW	er, Asug	<u>imansim,</u>	Refractive		Astigmatism	Resolvin	n	
Number	Model Numb	er	Eye	(diopte		(diopters)	Power	Pass/Fail	
	ACDEN C4	_	Left	0.02		0.01	28		
135449-01	ASPEN G1	5	Right	0.02		0.01	28	Pass	
105110.00	ASPEN GO	ASPEN GOLD MIRROR		0.00	0.03		28	5	
135449-02				0.00		0.03	28	Pass	
Section 5.1.4	Section 5.1.4 Prism and Prism Imbalance								
				Vertical			e Out		
Control	Model	_	Prism				alance	D (E :)	
Number	Number	Eye	<u>(Δ)</u>	(Δ)	(Δ	.) (Δ)	Pass/Fail	
135449-01	ASPEN G15	Left Right	0.07 0.10	-0.03	-0.0)6 -		Pass	
	ASPEN	Left	0.09						
135449-02	GOLD		5.00	0.13		- 0	.06	Pass	
	MIRROR	Right	0.06						
Transmittance Ratings									
		ole Light mittance		UV Transr	Transmittance (%)				
Number	Model Number			(%)	L-Scale	Far UV	Near U\	/ U-Scale	
135449-01	ASPEN G15	Left Right		14.6 14.6	L3	0.00	0.00	U6	
	ASPEN GOLD	Left		10.5					
135449-01	MIRROR	Right		10.2	L3	0.00	0.00	U6	

Date: April 9, 2013



PHOTO OF SAMPLE(S):

ASPEN G15



ASPEN GOLD MIRROR



In Charge Of Tests:

Denis Niggli Engineer

Lighting Division

Report Reviewed By:

David Ellis

Senior Project Engineer

Date: April 9, 2013

Lighting Division